



成形材料	難燃ABS	POM
樹脂温度	220°	190°
射出圧力	1650kg	1400kg
金型温度	60°	60°